



Material Properties	Imperial	Metric
Yield Stress, Minimum (psi [kPa])	110,000	758,423
Yield Stress, Maximum (psi [kPa])	140,000	965,266
Tensile Stress, Minimum (psi [kPa])	125,000	861,845
Hardness, Maximum (HRC [HBW])	N/A	N/A
Pipe Dimensions & Weight		
Outside Diameter, Nominal (in [mm])	2.375	60.33
Weight, Nominal (lbm/ft [kg/m])	5.95	8.85
Wall Thickness, Nominal (in [mm])	0.254	6.45
Inside Diameter, Nominal (in [mm])	1.867	47.42
API Drift Diameter (in [mm])	1.773	45.04
Upset-End Diameter, Nominal (in [mm])	N/A	N/A
Upset-End Length, Minimum (in [mm])	N/A	N/A
Cross Sectional Area, Nominal (sq.in. [sq.mm])	1.692	1091.61
Pipe Load Capacities		
Tensile Yield (lbf [N])	186,100	827,814
Internal Yield Pressure (psi [kPa])	20,590	141,963
Collapse Pressure (psi [kPa])	21,010	144,859
Torsional Yield (lbf-ft [N.m])	8,600	11,660
Hydrostatic Test Pressure (psi [kPa])	10,000	68,948
Bending rate (°/100 ft [°/30 m])	212	209
Connection Dimensions		
Coupling OD (in [mm])	3.092	78.54
Coupling Replacement Limit OD (in [mm])	2.967	75.36
Connection ID (in [mm])	1.805	45.85
Coupling Length, Minimum (in [mm])	7.700	195.58
Make-up Loss (in [mm])	3.441	87.40
Tool-Joint OD (in [mm])	2.905	73.79
Connection Torque Capacities		
Low Shoulder Torque (lbf-ft[N.m])	300	410
High Shoulder Torque (lbf-ft[N.m])	1,500	2,030
Minimum Make-up Torque (lbf-ft[N.m])	2,000	2,710
Optimum Make-up Torque (lbf-ft [N.m])	4,250	5,760
Maximum Make-up Torque (lbf-ft [N.m])	6,500	8,810
Datable of Torque (In it [iv.iii])	0,000	11 //0

^{**} Listed Rotating / Yield Torques and Connection Load Capacities have to be recalculated for Special Clearance OD.

Material is EMI/SEA inspected to 5% notch, over OD/ID, long/trans and wall thickness orientations, per API/ASTM requirements.

Extended Reach Work-Over Connection

SIZE: 2.375 inch [60.33 mm]
WEIGHT: 5.95 lbm/ft [8.85 kg/m]

GRADE: P-110

Hi-Torque, Double-Start, Straight-to-Taper, NJO Hook Thread, Threaded & Coupled Joint

Connection Load Capacities	
Tensile Efficiency (% of pipe body)	115
Internal Yield Pressure (psi)	40,060
External Yield pressure (psi)	36,260
Leak Resistance Pressure (psi)	radial m2m seal
Compression Efficiency (% of pipe body)	115
Torque Efficiency (% of pipe body)	105
Bending Strength Ratio (BSR)	1.79



All the information provided is general data. Depicted colors and markings may differ from actual product. This is not any kind of warranty/quality certificate. Tejas Tubular has the right to change this data at any time for product improvement. This is a non-controlled document. TTRS1, TTRS1-HT, TTXS, TTXS-HT, TTNY, TTNY-HP, TTUS, TTUS-HT, TTXU, TTS-8, TTS-8 CI, TTS-8 CIGL, TTS-8s, TTS-6, TTS-6, TTS-6, TTS-6, TTS-6, TTS-7, TTIJ, TTWS, TTWS2, TTWS-IJ, SABERTOOTH, GOBLIN, EUXT and the Tejas Tubular logo are marks of Tejas Tubular Products, Inc.

11,660

12,200

Rotating Torque* (lbf-ft [N.m])

Yield Torque (lbf-ft [N.m])

8,600

9,000