

TTS-8CIGL

Two-step Corrosion Inhibitor Glass Liner Tubing Connection

Material Properties	Imperial	Metric
Yield Stress, Minimum (psi [kPa])	80,000	551,581
Yield Stress, Maximum (psi [kPa])	95,000	655,002
Tensile Stress, Minimum (psi [kPa])	95,000	655,002
Hardness, Maximum (HRC [HBW])	23	241
Pipe Dimensions & Weight		
Outside Diameter, Nominal (in [mm])	2.875	73.03
Weight, Nominal (lbm/ft [kg/m])	6.50	9.67
Wall Thickness, Nominal (in [mm])	0.217	5.51
Inside Diameter, Nominal (in [mm])	2.441	62.00
API Drift Diameter (in [mm])	2.347	59.62
Upset-End Diameter, Minimum (in [mm])	3.329	84.56
Upset-End Length, Minimum (in [mm])	4.250	107.95
Cross Sectional Area, Nominal (sq.in. [sq.mm])	1.812	1169.03
Pipe Load Capacities		
Tensile Yield (lbf [N])	145,000	644,992
Internal Yield Pressure (psi [kPa])	10,570	72,878
Collapse Pressure (psi [kPa])	11,170	77,014
Torsional Yield (lbf-ft [N.m])	8,620	11,690
Hydrostatic Test Pressure (psi [kPa])	9,700	66,879
Bending rate (°/100 ft [°/30 m])	128	126
Connection Dimensions		
Connection OD (in [mm])	3.210	81.53
Special Clearance** OD (in [mm])	3.166	80.42
Connection ID (in [mm])	2.366	60.10
Coupling Length, Minimum (in [mm])	N/A	N/A
Make-up Loss (in [mm])	2.390	60.71
Threads per Inch (pitch [mm]	8.000	3.18
Connection Torque Capacities		
Low Shoulder Torque (lbf-ft[N.m])	370	500
High Shoulder Torque (lbf-ft[N.m])	1,850	2,510
Minimum Make-up Torque (lbf-ft[N.m])	2,100	2,850
Optimum Make-up Torque (lbf-ft [N.m])	2,400	3,250
Maximum Make-up Torque (lbf-ft [N.m])	2,600	3,530
Rotating Torque (lbf-ft [N.m])	5,500	7,460
Yield Torque (lbf-ft [N.m])	6,900	9,360

^{**} Listed Rotating / Yield Torques and Connection Load Capacities have to be recalculated for Special Clearance OD.

Material is EMI/SEA inspected to 10% notch, over OD/ID, long/trans and wall thickness orientations, per API/ASTM requirements.

SIZE: 2.875 inch [73.03 mm]
WEIGHT: 6.5 lbm/ft [9.67 kg/m]

GRADE: L-80

CS look-alike, with an internal corrosion inhibitor coating, reinforced by fiberglass liner and a teflon seal ring, for highly corrosive sour/sweet applications, in which you want a ruggedized ID

Connection Load Capacities	
Tensile Efficiency (% of pipe body)	118
Internal Yield Pressure (% of pipe body)	100
External Yield pressure (psi)	18,270
Leak Resistance Pressure (psi)	radial m2m seal
Compression Efficiency (% of pipe body)	118
Torque Efficiency (% of pipe body)	80
Bending Strength Ratio (BSR)	1.30



All the information provided is general data. Depicted colors and markings may differ from actual product. This is not any kind of warranty/quality certificate. Tejas Tubular has the right to change this data at any time for product improvement. This is a non-controlled document. TTRS1, TTRS1-HT, TTXS, TTXS-HT, TTUS, TTUS-HT, TTXU, TTS-8, TTS-8 CI, TTS-8 CIGL, TTS-6, TTS6-Black, TTIB, TTIJ, TTFJ, TTWS, TTWS-Black, SABERTOOTH, GOBLIN, SPEARHEAD, EUXT and the Tejas Tubular logo are marks of Tejas Tubular Products, Inc.